



# 糖厂专用活性炭

## ACTIVATED CARBON FOR SUGAR INDUSTRY



### 糖脱色活性炭

#### Activated Carbon for Sugar Industry

压块破碎炭,以精选多种煤为原料,经配煤,磨粉,压块等多种工艺加工而成。

此产品性能稳定,中微孔发达,亚甲蓝高,灰分低,零漂浮,吸附能力强,吸附容量大,截污能力好,再生损耗较低。

广泛应用于糖厂,葡萄糖厂,乳酸发酵厂,味精厂,医药厂,污水处理厂,柠檬酸厂的脱色和精制。

Crushed activated carbon, which raw material is more than one kind of selected bituminous coals, is made by the process of blending, powdering, briquetting and other steps.

The advantages are stable performance, developed micropores and mesopores, high methylene blue, low ash content, zero floatage, high adsorbing ability, large adsorbing volume, nice entrapment capacity, and low loss in regeneration process.

The products are widely used in food, beverage, medicine, tap water, sugar, oil and other industries, in brewing, sewage treatment, power plants, electroplating, pharmaceutical factory, citric acid plant decolorization refining and MSG factory,



### 糖厂活性炭 Activated Carbon for Sugar Industry

指标 Spec 型号 Type	粒径 Particle size mm	糖蜜值 Molasses Number	焦糖脱色 Caramel Decoloration	碘值 Iodine No. mg/g	灰分 Ash %	水分 Moisture content %	PH	亚甲蓝 MB mg/g	铁 Fe <sup>+</sup> %
ZLGC-1240	1.6--0.45	200--230	82--90	900--1000	≤8.0	≤10	6--7	160--230	0.01--0.03
ZLGC-830	2.5--0.6	200--230	82--90	900--1000	≤8.0	≤10	6--7	160--230	0.01--0.03

For more information or to contact Zhulin visit: [www.zhulincarbon.com](http://www.zhulincarbon.com)

NOTICE Due to the progressive nature of the Zhulin Carbons Group and the continually improving design and performance of our products, we reserve the right to change product specifications without prior notification. The information contained in this datasheet is intended to assist a customer in the evaluation and selection of products supplied by Zhulin Carbons. The customer is responsible for determining whether products and the information contained in this document are appropriate for customer's use. Zhulin Carbons assumes no obligation or liability for the usage of the information in this datasheet, no guarantees or warranties, expressed or implied, are provided. Zhulin Carbons disclaims responsibility and the user must accept full responsibility for performance of systems based on this data.

Zhulin Activated Carbon Group

No.6 Huangyang Street High-tech Development Zone  
Zhengzhou China

TEL: +86-0371-56071169  
FAX: +86-0371-69651710  
Email: [info@zhulincarbon.com](mailto:info@zhulincarbon.com)  
Web: [www.zhulincarbon.com](http://www.zhulincarbon.com)

